

NEUTHANE 3200/765 Series

MDI – Ester Rotational Casting Systems

Published August 2024 Version 3

The NEUTHANE 3200/765 series are high performance MDI – ester rotational casting systems designed to produce roller coverings for use in arduous application areas.

- a high level of physical properties
- good dynamic performance
- very good cut and abrasion resistance
- very good chemical resistance
- non MOCA curatives
- no moulds for processing
- room temperature curing

Typical

Applications

Steel mill rollers (dry applications)
Paper mill rollers (dry applications)

Processing

- Avoid prolonged storage of prepolymers at elevated temperatures. This will result in low hardness and lower properties of the cured material
 - Avoid moisture contamination of all materials
 - Part used containers should be flushed with dry nitrogen and resealed immediately after use
 - To prevent de-lamination, subsequent layers should be applied within 30 minutes
1. Melt prepolymer at 50-70°C for 12-24 hours
 2. Heat the prepolymer and curative to the recommended temperature
 3. Ensure that the curative is thoroughly mixed prior to use (the storage tank on the machine should be fitted with agitation to prevent separation during use)
 4. Degass to remove air
 5. Dispense at 700-2000g per minute*
 6. Adjust rotation and traverse speed until a smooth build up is achieved*
 7. Cure as recommended

* This will vary depending upon diameter of roller. As a general guide the output rate, rotational and traverse speeds will all increase as the diameter of the roller increases

Alternatives

Wet / Dynamic Applications	- PTMEG ether-based systems	NEUTHANE 3100 [MDI rotational casting]
----------------------------	-----------------------------	--

Neuthane 3200/765 MDI – Ester Rotational Casting Systems (70 Shore A – 80 Shore A)

NEUTHANE GRADE			3200/765	3200/765	3200/765
NEUTHANE CURATIVE			3270/765	3275/765	3280/765
Mix Ratio: Curative per 100 Parts resin	by weight		52.6	45.5	40.5
Resin Temperature	°C		75	75	75
Curative Temperature	°C		40	40	40
Recommended Roller Temperature	°C		Room Temperature	Room Temperature	Room Temperature
Viscosity @ 100°C	Curative	cPs	800	800	800
Pot life (on a 500g mix)	seconds		20-30	20-30	20
Recommended Cure Temperature / Time	°C / Days		Minimum 20 / 48	Minimum 20 / 48	Minimum 20 / 48

Hardness	ISO 48-4	Shore A	70	75	80
	ISO 48-4	Shore D	-	-	-
100% Modulus	ISO 37	lb/in ² (MPa)	330 (2.3)	470 (3.2)	840 (5.8)
300% Modulus	ISO 37	lb/in ² (MPa)	600 (4.1)	800 (5.5)	1180 (8.1)
Tensile Strength	ISO 37	lb/in ² (MPa)	6300 (43.5)	6380 (44.0)	6900 (47.6)
Elongation at Break	ISO 37	%	600	600	550
Tear (Die C)	ISO 34-1	lbf/in (kN/m)	300 (52.5)	350 (61.3)	410 (71.8)
Specific Gravity		g / cm ³	1.21	1.22	1.23

Data above represents typical physical properties. Since conditions of use are beyond our control, no warranty is given or implied in respect of any recommendations or suggestions made by ourselves, nor is freedom from patent infringement inferred.

